

GB 1460864
JAN 1977GROUP 3.51
CLASS 285
RECORDED

ICATION

1460864

1 460 864

- (21) Application No. 11308/74 (22) Filed 14 March 1974
 (23) Complete Specification filed 13 June 1975
 (44) Complete Specification published 6 Jan. 1977
 (51) INT CL⁷ F16L 19/00
 (52) Index at acceptance F2G 25A 2B
 (72) Inventors JACK BEACHAM and BRIAN BERNARD DEELEY

GREAT BRITAIN (19)
 GROUP 3.51
 CLASS 285
 RECORDED



(54) IMPROVEMENTS IN PIPE UNIONS

(71)

PANY LII

Delta Road

hereby dec

5 pray that a

the method

be particu

following s

This inve

10 providing

first and set

which the

more partic

comprising

15 flange and

member hi

adjacent to

being adap

with the fir

20 of the tub

member by co-operation between the

flanges of the nut and the tubular

member on tightening of the union

nut onto the first member, and a

25 further metallic member secured to the

other end of the tubular member and

adapted to screw-threadedly engage with

the second screw-threaded member, the

30 member by the flange on the tubular

member and said further member which has

a sufficiently large transverse dimension to

prevent passage of the union nut over said

further member.

35 Unions of this kind have been used for

connecting gas appliances together, for

connecting a meter service governor to a

meter for example.

40 It is known to connect the tubular member

to said further member after assembly of the

union nut onto the tubular member by

screwing and brazing the tubular member to

said further member.

45 This is, however, an expensive operation,

requires testing of the seal between the two

members, and has a high reject rate.

Moreover the seal between the two

members may be broken when the union is

SPEY

Q67

*A1007Y/01 *GB 1460-864

Mfg. pipe union for incompatible threaded members - by threading
 tubular member, fitting union nut, screwing end member on and
 deforming threaded joint


SPERRY & CO LTD 14.03.74-GB-011308

(06.01.77) F16L19

A pipe union for two incompatible threaded members is
 formed from a stamped union nut (1) held captive on a sta-

mped and machined tubular member (2) secured to a forged member (3).
 The nut is tapped and the member (3) has an external tapered thread (6).
 The union is formed by first forming a thread on one end of the tubular member (2) and then passing the nut over this end. The member (3) is then screwed onto the tubular member and a ball plunger or roller burnishing tool inserted to expand the

joint to bind the threads of the joint together to form a gas tight seal. 13.6.75 (4pp)



tion of the

50

method of

and set forth

end of the

ter member

threads, 55

the tubular

other end,

er to said

permanently

int between 60

aid further

radially.

the further

a drop of a

applied to 65

ber at said

other end is formed with an external screw

thread for engagement with a co-operating

internal screw thread formed in said further

member. 70

Usually the further member will be

formed with an external radially extending

polygonal flange for engagement by a

spanner when the further member is

tightened in use to the second member. It is

this polygonal flange which would prevent

assembly of the union nut onto the tubular

member if the tubular member were to be

made integral with the further member. 80

The tubular member and the further

member may be made of any suitable metal

but preferably they are made of brass.

The expansion of the joint between the

tubular member and the further member is

conveniently performed by cold forming

with a ball plunger or roller burnishing tool. 85

The invention will now be further

described, by way of example only, with

reference to the accompanying drawing

which is an axial cross section of a com- 90

pleted brass union adapted to secure an

externally screw-threaded first member to an

internally screw-threaded second

member to provide fluid communication 95

therebetween.

BEST AVAILABLE COPY

The union comprises a stamped union nut 1 held captive on a stamped and machined tubular member 2 secured to a further member 3 which is a forging.

5 The union nut 1 is internally screw-threaded for engagement with external screw threads on a first member, not shown, and is provided with an internal radial flange 4 for engagement with an external radial flange 5 which is an integral part of one end of the tubular member 2. When the union nut 1 is screwed in use onto the first member the tubular member 2 is drawn towards the first member by the engagement between the flanges 4 and 5.

15 The further member 3 is formed with an external tapered screw thread 6 for engagement with an internal co-operating screw thread of a second member, not shown, and is provided with an integral polygonal radial flange 7 for engagement by a spanner during tightening in use of the further member 7 to the second member.

20 Initially the other end 8 of the tubular member 3 comprises a plain sleeve. Prior to assembly of the union nut 1 onto the sleeve the exterior of said other end 8 is formed with a plain external screw thread for engagement with a complementary screw thread formed internally of the further member 3. The union nut is then assembled onto the tubular member 2 by passing it over said other end 8 of the tubular member. The tubular member and the further member are then screwed together and a ball plunger or roller burnishing tool is inserted into the joint between the members by passing it through the further member 3, and the joint between the members is expanded radially over the distance A by cold forming to increase the internal diameter D of the joint and to bind the screw threads of the joint together to form a gas-tight seal between the tubular member 2 and the further member 3.

45 In one example the initial diameter D is 0.875 inches and a plunging tool of 0.925 inch diameter is used. The diameter D is thus increased by slightly more than 4% of its initial value.

50 In order to increase the break-loose torque of the joint between the members 2 and 3 a drop of a screw-thread locking material such as that sold under the Registered Trade Mark 'LOCTITE' STULOCK (OR GRADE 75) is applied to the middle part of one of the screw threads before the members 2 and 3 are screwed together.

WHAT WE CLAIM IS:—

1. A method of manufacturing a pipe union of the kind set forth comprising forming said other end of the tubular member and said further member with complementary screw threads, assembling the union nut onto the tubular member by passing it over said other end of the tubular members, screwing said tubular member to said further member, and then permanently deforming the screw-threaded joint between said tubular member and said further member by expanding the joint radially.

2. The method according to claim 1 in which the tubular member is formed with its screw thread prior to assembling the union nut onto the tubular member.

3. The method according to claim 1 or claim 2 in which prior to screwing the tubular member to said further member screw-thread locking material is applied to at least one of the co-operating screw threads.

4. The method according to any of the preceding claims in which the co-operating screw threads comprise an external screw thread formed on the tubular member and an internal screw thread formed on said further member.

5. The method according to any of the preceding claims in which the expansion of the joint is performed by cold forming.

6. The method according to claim 5 in which the joint between the tubular member is expanded by insertion of a ball plunger.

7. The method according to claim 5 in which the joint between the tubular member is expanded by a roller burnishing tool.

8. The method according to any of the preceding claims in which the tubular member and said further member are of brass.

9. The method according to any of the preceding claims in which the internal diameter of the joint between the tubular member and said further member is increased by more than four per cent of the initial diameter.

10. The method according to claim 1 and substantially as described with reference to the accompanying drawing.

11. A pipe union of the kind set forth produced by the method according to any of the preceding claims.

12. A pipe union of the kind set forth manufactured according to the method of claim 10 and substantially as described with reference to the accompanying drawing.

BEST AVAILABLE COPY

The union comprises a stamped union nut 1 held captive on a stamped and machined tubular member 2 secured to a further member 3 which is a forging.

5 The union nut 1 is internally screw-threaded for engagement with external screw threads on a first member, not shown, and is provided with an internal radial flange 4 for engagement with an external radial flange 5 which is an integral part of one end of the tubular member 2. When the union nut 1 is screwed in use onto the first member the tubular member 2 is drawn towards the first member by the engagement between the flanges 4 and 5.

15 The further member 3 is formed with an external tapered screw thread 6 for engagement with an internal co-operating screw thread of a second member, not shown, and is provided with an integral polygonal radial flange 7 for engagement by a spanner during tightening in use of the further member 7 to the second member.

20 Initially the other end 8 of the tubular member 3 comprises a plain sleeve. Prior to assembly of the union nut 1 onto the sleeve the exterior of said other end 8 is formed with a plain external screw thread for engagement with a complementary screw thread formed internally of the further member 3. The union nut is then assembled onto the tubular member 2 by passing it over said other end 8 of the tubular member. The tubular member and the further member are then screwed together and a ball plunger or roller burnishing tool is inserted into the joint between the members by passing it through the further member 3, and the joint between the members is expanded radially over the distance A by cold forming to increase the internal diameter D of the joint and to bind the screw threads of the joint together to form a gas-tight seal between the tubular member 2 and the further member 3.

45 In one example the initial diameter D is 0.875 inches and a plunging tool of 0.925 inch diameter is used. The diameter D is thus increased by slightly more than 4% of its initial value.

50 In order to increase the break-loose torque of the joint between the members 2 and 3 a drop of a screw-thread locking material such as that sold under the Registered Trade Mark 'LOCTITE' 55 STUDLOCK (OR GRADE 75) is applied to the middle part of one of the screw threads before the members 2 and 3 are screwed together.

WHAT WE CLAIM IS:—

1. A method of manufacturing a pipe union of the kind set forth comprising forming said other end of the tubular member and said further member with complementary screw threads, assembling the union nut onto the tubular member by passing it over said other end of the tubular members, screwing said tubular member to said further member, and then permanently deforming the screw-threaded joint between said tubular member and said further member by expanding the joint radially.

2. The method according to claim 1 in which the tubular member is formed with its screw thread prior to assembling the union nut onto the tubular member.

3. The method according to claim 1 or claim 2 in which prior to screwing the tubular member to said further member screw-thread locking material is applied to at least one of the co-operating screw threads.

4. The method according to any of the preceding claims in which the co-operating screw threads comprise an external screw thread formed on the tubular member and an internal screw thread formed on said further member.

5. The method according to any of the preceding claims in which the expansion of the joint is performed by cold forming.

6. The method according to claim 5 in which the joint between the tubular member is expanded by insertion of a ball plunger.

7. The method according to claim 5 in which the joint between the tubular member is expanded by a roller burnishing tool.

8. The method according to any of the preceding claims in which the tubular member and said further member are of brass.

9. The method according to any of the preceding claims in which the internal diameter of the joint between the tubular member and said further member is increased by more than four per cent of the initial diameter.

10. The method according to claim 1 and substantially as described with reference to the accompanying drawing.

11. A pipe union of the kind set forth produced by the method according to any of the preceding claims.

12. A pipe union of the kind set forth manufactured according to the method of claim 10 and substantially as described with reference to the accompanying drawing.

BARKER, BRETTELL & DUNCAN
Chartered Patent Agents
Agents for the Applicants
138 Hagley Road
Edgbaston
Birmingham B16 9PW.

Printed for Her Majesty's Stationery Office by the Courier Press, Leamington Spa, 1977.
Published by the Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from
which copies may be obtained.

BEST AVAILABLE COPY